



BSI Standards Publication

<https://www.china-gauges.com/>

Copper and copper alloys — Hollow rod for free machining purposes

National foreword

This British Standard is the UK implementation of EN 12168:2024. It supersedes BS EN 12168:2016, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee NFE/34, Copper and copper alloys.

A list of organizations represented on this committee can be obtained on request to its committee manager.

Contractual and legal considerations

This publication has been prepared in good faith, however no representation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability is or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient's own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

This publication has been prepared under a mandate given to the European Standards Organizations by the European Commission and the European Free Trade Association. It is intended to support requirements of the EU legislation detailed in the European Foreword. A European Annex, usually Annex ZA or ZZ, describes how this publication relates to that EU legislation.

For the Great Britain market (England, Scotland and Wales), if UK Government has designated this publication for conformity with UKCA marking (or similar) legislation, it may contain an additional National Annex. Where such a National Annex exists, it shows the correlation between this publication and the relevant UK legislation. If there is no National Annex of this kind, the relevant Annex ZA or ZZ in the body of the European text will indicate the relationship to UK regulation applicable in Great Britain. References to EU legislation may need to be read in accordance with the UK designation and the applicable UK law. Further information on designated standards can be found at www.bsigroup.com/standardsandregulation.

For the Northern Ireland market, UK law will continue to implement relevant EU law subject to periodic confirmation. Therefore Annex ZA/ZZ in the European text, and references to EU legislation, are still valid for this market.

UK Government is responsible for legislation. For information on legislation and policies relating to that legislation, consult the relevant pages of www.gov.uk.

© The British Standards Institution 2024
Published by BSI Standards Limited 2024

ISBN 978 0 539 20214 4

ICS 77.150.30

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 October 2024.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

<https://www.china-gauges.com/>

<https://www.china-gauges.com/>

EUROPEAN STANDARD

EN 12168

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2024

ICS 77.150.30

Supersedes EN 12168:2016

English Version

Copper and copper alloys - Hollow rod for free machining purposes

Civre et alliages de cuivre - Barres creuses pour
décolletageKupfer und Kupferlegierungen - Hohlstangen für die
spanende Bearbeitung

This European Standard was approved by CEN on 30 June 2024.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

	Page
European foreword.....	4
Introduction	6
1 Scope.....	7
2 Normative references.....	7
3 Terms and definitions	7
4 Designations.....	9
4.1 Material.....	9
4.1.1 General.....	9
4.1.2 Symbol.....	9
4.1.3 Number	9
4.2 Material condition	9
4.3 Product.....	9
5 Ordering information	12
6 Requirements.....	14
6.1 Composition	14
6.2 Mechanical properties.....	14
6.3 Resistance to dezincification	14
6.4 Residual stress level.....	14
6.5 Dimensions and tolerances	14
6.5.1 Diameter or width across-flats.....	14
6.5.2 Tolerance on wall thickness.....	14
6.5.3 Eccentricity.....	15
6.5.4 Shape tolerances	15
6.5.5 Straightness.....	15
6.5.6 Length.....	15
6.5.7 Corner radii	15
6.5.8 Twist of polygonal hollow rod.....	16
6.6 Surface quality.....	16
6.7 Internal inclusion.....	17
7 Sampling.....	17
7.1 General.....	17
7.2 Analysis.....	17
7.3 Mechanical tests	17
7.4 Dezincification resistance and stress corrosion resistance tests.....	17
8 Test methods	18
8.1 Analysis.....	18
8.2 Tensile test	18
8.2.1 General.....	18
8.2.2 Location of test pieces	18
8.2.3 Shape and size of test pieces	18
8.2.4 Procedure for testing.....	18
8.2.5 Determination of results	18

8.3	Hardness test.....	18
8.4	Dezincification resistance test.....	19
8.5	Stress corrosion resistance test	19
8.6	Retests	19
8.6.1	Analysis, tensile, hardness and dezincification resistance tests.....	19
8.6.2	Stress corrosion resistance test	19
8.7	Rounding of results.....	19
9	Certificate of Compliance and inspection documentation.....	20
9.1	Certificate of Compliance	20
9.2	Inspection documentation	20
10	Marking, packaging, labelling	20
Annex ZA (informative) Relationship between this European Standard and the essential requirements of Directive 2014/68/EU (Pressure equipment Directive) aimed to be covered.....		39
Bibliography		40

European foreword

This document (EN 12168:2024) has been prepared by Technical Committee CEN/TC 133 “Copper and copper alloys”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2025, and conflicting national standards shall be withdrawn at the latest by April 2025.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12168:2016.

In comparison with EN 12168:2016, the following significant technical changes were made:

- a) Modification of the note in Clause 1;
- b) Introduction of eddy current test parameters in 6.6;
- c) Introduction of 6.7 Internal inclusion;
- d) Modification of the definition of diameter or width across-flats in 6.5.4.1;
- e) Addition of a new Figure for straightness at 6.5.5 and modification of values in Table 13;
- f) Introduction in the chemical composition Tables of a footnote to explain the meaning of elements for which no upper and lower limits are specified;
- g) Deletion of alloys groups in Table 3;
- h) Modification of the chemical composition of CuZn39Pb3 (CW614N), CuZn40Pb2 (CW617N), CuZn35Pb1,5AlAs (CW625N) and CuZn33Pb1,5AlAs (CW626N) in Table 3;
- i) Addition of a new alloy CuZn40Pb1 (CW627N) in Table 3 and Table 7;
- j) Modification of the chemical composition of CuZn33Pb1AlSiAs (CW725R) in Table 4;
- k) Addition of a new alloy CuZn36Si1P (CW726R) in Table 4 and Table 8;
- l) Modification of the range of dimensions in Table 9 and in Table 11;
- m) Addition of Table 18 and Table 19;
- n) Addition of Annex ZA.

This document is one of a series of European Standards for the copper and copper alloy products rod, wire, profile and forgings. Other products are specified as follows:

- EN 12163, *Copper and copper alloys — Rod for general purposes*;
- EN 12164, *Copper and copper alloys — Rod for free machining purposes*;
- EN 12165, *Copper and copper alloys — Wrought and unwrought forging stock*;

- EN 12166, *Copper and copper alloys — Wire for general purposes*;
- EN 12167, *Copper and copper alloys — Profiles and bars for general purposes*;
- EN 13601, *Copper and copper alloys — Copper rod, bar and wire for general electrical purposes*;
- EN 13602, *Copper and copper alloys — Drawn, round copper wire for the manufacture of electrical conductors*;
- EN 13605, *Copper and copper alloys — Copper profiles and stranded wire for electrical purposes*.

This document has been prepared under a standardisation request addressed to CEN by the European Commission. The Standing Committee of the EN/A States subsequently approves these requests for its Member States.

For the relationship with EU Legislation, see informative Annex ZA, which is an integral part of this document.

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Introduction

The European Committee for Standardization (CEN) draws attention to the fact that it is claimed that compliance with this document may involve the use of a patent concerning the alloy CuZn36Si1P (CW726R) given in 6.1.

CEN takes no position concerning the evidence, validity and scope of this patent right.

The holder of this patent right has ensured the CEN that he is willing to negotiate licenses under reasonable and non-discriminatory terms and conditions with applicants throughout the world. In this respect, the statement of the holder of this patent right is registered with CEN.

— For CuZn36Si1P (CW726R) information may be obtained from:

Luvata Oy
Kuparitie 5
28330 Pori
FINLAND

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights other than those identified above. CEN shall not be held responsible for identifying any or all such patent rights.

CEN and CENELEC maintain online lists of patents relevant to their standards. Users are encouraged to consult the lists for the most up to date information concerning patents (<https://www.cencenelec.eu/european-standardization/ipr-and-patents/patents/>).

Due to developing legislation, the composition of a material may be restricted to the composition specified in this European Standard with respect to individual uses (e.g. for the use in contact with drinking water in some Member States of the European Union). These individual restrictions are not part of this European Standard. Nevertheless, for materials for which traditional and major uses are affected, these restrictions are indicated. The absence of an indication, however, does not imply that the material can be used in any application without any legal restriction.

1 Scope

This document specifies the composition, property requirements and dimensional tolerances for copper alloy hollow rod, finally produced by drawing or extruding, specifically intended for free machining purposes.

NOTE Hollow products having an outside diameter greater than 80 mm and/or a wall thickness less than 2 mm are most frequently specified in EN 12449.

The sampling procedures, the methods of test for verification of conformity to the requirements of this document, are also specified.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 764-5:2014, *Pressure equipment — Part 5: Inspection documentation of metallic materials and compliance with the material specification*

EN 10204:2004, *Metallic products — Types of inspection documents*

EN 14977:2006, *Copper and copper alloys — Detection of tensile stress — 5 % ammonia test*

EN 17263:2019, *Copper and copper alloys — Eddy current testing on the outer surface of rods, bars, hollow rods and wires for the detection of defects by encircling test coil*

EN ISO 6506-1:2014, *Metallic materials — Brinell hardness test — Part 1: Test method (ISO 6506-1:2014)*

EN ISO 6507-1:2018, *Metallic materials — Vickers hardness test — Part 1: Test method (ISO 6507-1:2018)*

EN ISO 6509-1:2014, *Corrosion of metals and alloys — Determination of dezincification resistance of copper alloys with zinc — Part 1: Test method (ISO 6509-1:2014)*

EN ISO 6892-1:2019, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1:2019)*

ISO 6957:1988, *Copper alloys — Ammonia test for stress corrosion resistance*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1
hollow rod

straight product, of uniform cross-section along its whole length with an enclosed void for which the longitudinal axes of its external contour and its internal contour, which is the boundary with the enclosed void, are coincidental

Note 1 to entry: The external and internal contours of the rod, at any cross-section, can be that of a circle, square, rectangle, hexagon, or octagon, or with slight modification of those basic shapes by inclusion of detail(s) of relatively small size to the remainder of the cross-section. Examples of hollow rod cross-sections are shown in Figure 1.




Figure 1 — Examples of hollow rod cross-sections

3.2
deviation from circular form

difference between the maximum and the minimum outside diameters measured at any one cross-section of the product

3.3
eccentricity

difference between the maximum and the minimum wall thickness, measured in the same cross-section perpendicular to the axis of the hollow rod, expressed as a percentage of the sum of the maximum and minimum wall thicknesses ($s_{max.}$ and $s_{min.}$):

$$e = \frac{s_{max.} - s_{min.}}{s_{max.} + s_{min.}} \times 100$$

Note 1 to entry: For polygons, wall thickness is measured perpendicular to the mid-points of the flat outside surfaces.

4 Designations

4.1 Material

4.1.1 General

The material is designated either by symbol or by number (see Tables 1 to 4).

4.1.2 Symbol

The material symbol designation is based on the designation system given in ISO 1190-1:1982.

NOTE Although material symbol designations used in this standard might be the same as those in other standards using the designation system given in ISO 1190-1:1982, the detailed composition requirements are not necessarily the same.

4.1.3 Number

The material number designation is in accordance with the system given in EN 1412:2016.

4.2 Material condition

For the purposes of this document, the following designations, which are in accordance with the system given in EN 1173:2008, apply for the material condition:

- | | |
|------------|--|
| M | material condition for the product as manufactured without specified mechanical properties; |
| R... | material condition designated by the minimum value of tensile strength requirement for the product with mandatory tensile property requirements; |
| H... | material condition designated by the minimum value of hardness requirement for the product with mandatory hardness requirements; |
| S (suffix) | material condition for a product which is stress relieved. |

Products in the M or H... material condition may be specially processed (i.e. mechanically or thermally stress relieved) in order to lower the residual stress level to improve the resistance to stress corrosion and the dimensional stability on machining [see Clause 5 list entry l), list entry m) and 8.5].

Exact conversion between material conditions designated R... and H... is not possible.

Except when the suffix S is used, material condition is designated by only one of the above designations.

4.3 Product

The product designation provides a standardized pattern of designation from which a rapid and unequivocal description of a product can be conveyed in communication. It provides mutual comprehension at the international level with regard to products which meet the requirements of the relevant document.

The product designation is no substitute for the full content of the document.

The product designation for products to this document shall consist of:

- denomination (hollow rod);
- number of this European Standard (EN 12168);
- material designation, either symbol or number (see Tables 1 to 4);

- d) DW for compliance in the chemical composition according to the 4 MS Common Composition List. This information is mandatory in the case in which the product is used for drinking water applications according to the 4 MS Common Composition List and not to be given in other cases (see Bibliography [11]);
- e) material condition designation (see Tables 5 to 8);
- f) external and/or internal cross-sectional shape (the following designations shall be used as appropriate: RND for round, SQR for square, RCT for rectangular, HEX for hexagonal, OCT for octagonal, PFL for profile);
- g) nominal cross-sectional dimensions (see Clause 5, list entry g)) or, for profiles, the number of the profile or a fully dimensioned and toleranced drawing, and:
 - 1) tolerance class A, B or C added to the external dimension (see Table 9); and/or
 - 2) tolerance class A or B added to the bore diameter (see Table 11);
- h) wall thickness (the following designation shall be used for wall thickness: WT) (see Table 10);
- i) for square, hexagonal or octagonal external shape, the corner shape (the following designations shall be used as appropriate: SH for sharp, RD for rounded) (see Table 15).


A typical product designation is shown in the following examples.

EXAMPLE 1 Hollow rod for free machining purposes conforming to this document, in material designated either CuZn40Pb2 or CW617N, for standard applications, in material condition H090, round external shape and bore, nominal outside diameter 40 mm, tolerance Class B, and nominal wall thickness 10 mm will be designated as follows:

Hollow rod EN 12168 — CuZn40Pb2 — H090 — RND40B × WT10

or

Hollow rod EN 12168 — CW617N — H090 — RND40B × WT10



EXAMPLE 2 Hollow rod for free machining purposes conforming to this document, in material designated either CuZn40Pb2 or CW617N, for drinking water applications according to the 4 MS Common Composition List, in material condition H090, round external shape and bore, nominal outside diameter 40 mm, tolerance Class B, and nominal wall thickness 10 mm will be designated as follows:

Hollow rod EN 12168 — CuZn40Pb2 — DW — H090 — RND40B × WT10

or

Hollow rod EN 12168 — CW617N — DW — H090 — RND40B × WT10

Denomination

Number of European Standard

Material designation

For the use in contact with drinking water,
according to 4 MS Common Composition List,
(restriction in chemical composition)

Material condition designation

Cross-sectional shape, nominal cross-sectional dimensions in millimetres,
tolerance class, nominal wall thickness

EXAMPLE 3 Hollow rod for free machining purposes conforming to this document, in material designated either CuZn40Pb2 or CW617N, for standard applications, in material condition H090, hexagonal external shape, 60 mm nominal width across-flats dimension, tolerance Class A, round bore of nominal diameter 20 mm, tolerance Class B sharp corners, will be designated as follows:

Hollow rod EN 12168 — CuZn40Pb2 — H090 — HEX60A × RND20B — SH

or

Hollow rod EN 12168 — CW617N — H090 — HEX60A × RND20B — SH

Denomination

Number of European Standard

Material designation

Material condition designation

Cross-sectional shape, nominal cross-sectional dimensions in millimetres,
tolerance class for each dimension


Corner designation

EXAMPLE 4 Hollow rod for free machining purposes conforming to this document, in material designated either CuZn40Pb2 or CW617N, for drinking water applications according to the 4 MS Common Composition List, in material condition H090, hexagonal external shape, 60 mm nominal width across-flats dimension, tolerance Class A, round bore of nominal diameter 20 mm, tolerance Class B sharp corners, will be designated as follows:

Hollow rod EN 12168 — CuZn40Pb2 — DW — H090 — HEX60A × RND20B — SH

or

Hollow rod EN 12168 — CW617N — DW — H090 — HEX60A × RND20B — SH



<https://www.china-gauges.com/>

5 Ordering information

In order to facilitate the enquiry, order and confirmation of order procedures the following information shall be specified:

- a) mass of product required;
- b) denomination (hollow rod);
- c) number of this European Standard (EN 12168);
- d) material designation (see Tables 1 to 4);
- e) material condition designation (see 4.2 and Tables 5 to 8) if it is other than M;
- f) DW for compliance in the chemical composition according to the 4 MS Common Composition List. This information is mandatory in the case in which the product is used for drinking water applications according to the 4 MS Common Composition List and not to be given in other cases;
- g) nominal cross-sectional dimensions or, in the case of hollow profiles, by a fully dimensioned and toleranced drawing:

To define the nominal cross-sectional dimensions of a hollow rod, it should state one of the following:

- 1) the external dimensions and the wall thickness (tolerances given in Tables 9 and 10); or
 - 2) the internal dimensions and the wall thickness (tolerances given in Tables 11 and 10); or
 - 3) the external and internal dimensions (tolerances given in Tables 9 and 11) and the maximum eccentricity (tolerances given in Table 12); or
- h) whether:
- 1) class A, B or C tolerances shall apply to external dimensions (see Table 9); and/or

- 2) class A or B tolerances shall apply to internal dimensions (see Table 11); unless the choice of these tolerance classes is left to the discretion of the supplier;
- i) for hollow rod having a square, hexagonal or octagonal external shape, whether “sharp” or “rounded” corners are required unless the corner radii of the rod are left to the discretion of the supplier (see 6.5.7 and Table 13);
- j) length of product required. Normally hollow rod is supplied to “nominal length” tolerances (see 6.5.6 and Table 14);

It is recommended that the product designation, as described in 4.3, is used for items b) to j).

In addition, it shall also state on the enquiry and order any of the following, if required:

- k) whether the products according to 6.3, are required to pass a dezincification resistance test (see 8.4);
- l) whether the products are required to pass a stress corrosion resistance test. If so which test method shall be used (see 8.5), if the choice is not left to the discretion of the supplier.
- m) whether the products shall be supplied in a thermally stress relieved material condition;
- n) whether special surface quality is required (see 6.6);
- o) whether surface quality test is required (see 6.6) and the class;
- p) whether a Certificate of Compliance is required (see 9.1);
- q) whether an inspection document is required, and if so, which type (see 9.2);
- r) whether there are any special requirements for marking, packaging or labelling (see Clause 10).

EXAMPLE Ordering details for 1 000 kg of hollow rod for free machining purposes conforming to EN 12168, in material designated either CuZn40Pb2 or CW617N, for drinking water application according to the 4 MS Common Composition List, in material condition H090, round external shape, nominal outside diameter 40 mm, tolerance class B, and nominal wall thickness 10 mm, tolerance class A, nominal length 3 000 mm:

1 000 kg Hollow rod — CuZn40Pb2 — DW — H090 — RND40B × WT10A
EN 12168

— nominal length 3 000 mm

or

1 000 kg Hollow rod — CW617N — DW — H090 — RND40B × WT10A
EN 12168

— nominal length 3 000 mm

6 Requirements

6.1 Composition

The composition shall conform to the requirements for the appropriate material given in Tables 1 to 4.

Due to developing legislation, specific applications (see 4.3) may require restrictions on the chemical composition. In this case the limitations shall be specified in the ordering information (see Clause 5 f)).

6.2 Mechanical properties

The properties shall conform to the appropriate requirements given in Tables 5 to 8. The tests shall be carried out in accordance with 8.2 or 8.3.

6.3 Resistance to dezincification

This requirement only applies to materials that are declared resistant to dezincification.

The maximum depth of dezincification, in any direction, of CuZn38As (CW511L), CuZn36Pb2As (CW602N), CuZn32Pb2AsFeSi (CW709R), CuZn21Si3P (CW724R) and CuZn33Pb1AlSiAs (CW725R) products shall not exceed 100 μm . For the alloys CuZn35Pb1,5AlAs (CW625N), CuZn33Pb1,5AlAs (CW626N) the maximum depth of dezincification, in any direction, shall not exceed 200 μm .

The test shall be carried out in accordance with 8.4.

NOTE Shape and distribution of beta phase aggregates can influence the dezincification resistance of products. Special requirements relating to shape and distribution of β phase aggregates are subject to agreement between the involved parties

Products in alloys other than CuZn21Si3P (CW724R) shall be subjected to heat treatment approximately in the range 500 $^{\circ}\text{C}$ to 550 $^{\circ}\text{C}$.

Should the user need to heat the material out of the range before specified (i.e. soldering, brazing or welding operations) then advice should be sought from the supplier.

6.4 Residual stress level

Products ordered and supplied in the stress relieved condition (see 4.2, 2nd paragraph) shall show no evidence of cracking if tested. The tests shall be carried out in accordance with 8.5.

6.5 Dimensions and tolerances

6.5.1 Diameter or width across-flats

When specified at the time of the order (see Clause 5 list entry g)), external diameter or width across-flats at any point shall conform to the tolerances given in Table 9.

When specified at the time of the order (see Clause 5 list entry g)), internal diameter of the bore at any point shall conform to the tolerances given in Table 11.

For internal shape other than circle the tolerances are subject to agreement between the involved parties.

6.5.2 Tolerance on wall thickness

When specified at the time of the order (see Clause 5 list entry g)), the wall thickness shall conform to the tolerances given in Table 10. For hollow rod having a polygonal external shape, the wall thickness shall be measured at the centre of each flat.

6.5.3 Eccentricity

When specified at the time of the order (see Clause 5 list entry g)), the percentage eccentricity of hollow rod having a circular or polygonal external cross-section shall conform to Table 12.

6.5.4 Shape tolerances

6.5.4.1 Circular cross-sections

For hollow rod having a circular external cross-section and for circular bores, the deviation from circularity of their diameters (see 3.2) shall not exceed h in the appropriate range of the tolerance on diameter given in Tables 9 and 11 respectively.

6.5.4.2 Polygonal external cross-sections


For hollow rod having a polygonal external cross-section, the width across-flats at any one cross-section, measured at the centre of each pair of opposite faces, shall not differ by more than half the range of the tolerance given in Table 9.

6.5.5 Straightness

For hollow rod of length 1 000 mm or over, the deviation from straightness, defined as the curvature (depth of arc) against a datum line when the product is lying flat in a horizontal plane (see Figure 2), shall conform to the tolerances given in Table 13.

NOTE Outside this range, the deviation from straightness is subject to agreement between the involved parties.

Dimensions in millimetres



Key

- h_1 depth of arc in any length l_1 of 1000
- h_2 depth of arc in any length l_2 of 400

Figure 2 — Measurement of straightness

6.5.6 Length

Hollow rod shall be supplied as “nominal lengths”, generally in the preferred lengths given in Table 14, and shall conform to the tolerances in the table.

Subject to agreement between the involved parties, an agreed proportion of underlength hollow rod may be included in a consignment of “nominal lengths” hollow rod.


6.5.7 Corner radii

The corner radii of hollow rod having a square, hexagonal or octagonal external shape, shall conform to Table 15 [see Clause 5 list entry i)].

Except in cases of dispute, the corners should be measured directly, either by use of a gauge or an optical projector. In cases of dispute, the method by optical projector should be used.

6.5.8 Twist of polygonal hollow rod

The maximum permitted twist V (see Figure 3) of hollow rod having a square, hexagonal or octagonal external shape, as measured between two cross-sections along the rod, shall conform to Table 16.



Key

- 1 reference plane
- V twist
- W width across-flats

Figure 3 — Measurement of twist of polygonal hollow rod

6.6 Surface quality

The surfaces shall be clean and smooth. The hollow rods may have a superficial film of drawing lubricant or, if annealed or thermally stress relieved, a superficial, dull, iridescent oxide film, securely adherent on the surfaces.

Discontinuous irregularities on the surfaces of the hollow rods are permitted if they are within the dimensional tolerances.

Since surface discontinuities (cracks, overlapping, scale, isolated pores, pits, grooves, etc.) cannot be completely avoided during manufacturing (hot and cold formation, heat treatments, handling and storage) and since they are retained when drawing, agreements shall be made regarding surface quality.

If eddy current test is requested, the test method given in EN 17263:2019 shall be applied using reference standard according to Table 18 for hollow round rod. For polygonal hollow rod the reference standard shall be agreed between the involved parties.

The sensitivity is to be set in such a way that the smallest signal of the borehole(s) just exceeds the response threshold (acceptance level).

The surface quality of the products shall be one of the classes according to Table 19 where:

K_2 = ratio of the signal for the lower detection threshold to the signal for the normal detection threshold (normal acceptance level)

d_0 = a maximum density of defects referred to a pre-set length of 300 mm (L_0)

% of sensitivity = percentage of acceptance level

If single hollow rods are tested unexamined ends exist.

Other surface control methods can be used by agreement between the involved parties.

Special requirements (e.g. pickling, degreasing, etc.) relating to the surface quality shall be agreed between the involved parties [see Clause 5, list entry n)].

6.7 Internal inclusion

Freedom of internal inclusions cannot be ensured in any copper alloys.

7 Sampling

7.1 General

When required or for use in cases of dispute, an inspection lot shall be sampled in accordance with 7.2 to 7.4.

7.2 Analysis

The sampling rate shall be in accordance with Table 17. A test sample, depending on the analytical technique to be employed, shall be prepared from each sampling unit and used for the determination of the composition.

When preparing the test sample, care should be taken to avoid contaminating or overheating the test sample. Carbide tipped tools are recommended; steel tools, if used, should be made of magnetic material to assist in the subsequent removal of extraneous iron. If the test samples are in finely divided form (e.g. drillings, millings), they should be treated carefully with a strong magnet to remove any particles of iron introduced during preparation.

In cases of dispute concerning the results of analysis, the full procedure given in ISO 1811-2 should be followed.

Results may be used from analyses carried out at an earlier stage of manufacturing the product, e.g. at the casting stage, if the material identity is maintained and if the manufacturer can ensure the traceability of the product.

7.3 Mechanical tests

The sampling rate shall be in accordance with Table 17. Sampling units shall be selected from the finished products. The test samples shall be cut from the sampling units. Test samples, and test pieces prepared from them, shall not be subjected to any further treatment, other than any machining operations necessary in the preparation of the test pieces.

7.4 Dezincification resistance and stress corrosion resistance tests

The sampling rate which shall be applied to finished products shall be:

- for products that have been heat treated: one sampling unit per heat treatment batch;
- for products that have not been heat treated: in accordance with Table 17.

The test samples shall be cut from the sampling units. Test samples and test pieces prepared from them shall not be subjected to any further treatment, other than any machining operations necessary in the preparation of the test pieces.

8 Test methods

8.1 Analysis

Analysis shall be carried out on the test pieces, or test portions, prepared from the test samples obtained in accordance with 7.2. Except in cases of dispute, the analytical methods used shall be at the discretion of the supplier. In case of dispute the methods of analysis to be used shall be agreed between the disputing parties. For expression of results, the rounding rules given in 8.7 shall be used.

8.2 Tensile test

8.2.1 General

Tensile test pieces shall be prepared in accordance with 8.2.2 and 8.2.3 and the test shall be carried out in accordance with 8.2.4.

8.2.2 Location of test pieces

Test pieces shall be machined from one of the following locations in the test sample obtained in accordance with 7.3:

- a) for test samples from products up to and including 25 mm diameter, or width across-flats or equivalent cross-sectional area, the test piece shall be coaxial with the product;
- b) for test samples from products over 25 mm diameter, or width across-flats or equivalent cross-sectional area, the test piece shall be tested in full section or extracted from the wall of the hollow rod with the longitudinal axis parallel to that of the product. For thickness lower than 11 mm the test piece shall be a circumferential portion of the wall of the original hollow rod (longitudinal strip). For thickness greater than 11 mm a cylindrical test piece shall be obtained by machining the wall of the original hollow rod; the longitudinal axis of the test piece shall be mid-way between the internal and external surface.

8.2.3 Shape and size of test pieces

Test pieces shall be in accordance with EN ISO 6892-1:2019.

Elongation requirements for hollow rod of thickness are based on original gauge lengths of $5,65 \sqrt{S_0}$ mm (A), where S_0 is the original cross-sectional area of the test piece in square millimetres.

8.2.4 Procedure for testing

The tensile test shall be carried out in accordance with the method given in EN ISO 6892-1:2019.

8.2.5 Determination of results

The tensile strength and the elongation shall be determined from the tensile test results obtained in accordance with 8.2.4. For expression of results the rounding rules given in 8.7 shall be used.

8.3 Hardness test

Hardness shall be determined on test pieces cut from the test sample obtained in accordance with 7.3. The test shall be carried out in accordance with EN ISO 6506-1:2014 or EN ISO 6507-1:2018 and the impression/ indentation made on the cross-section of the product mid-way between the external and internal surfaces.

8.4 Dezincification resistance test

The test method given in EN ISO 6509-1:2014 shall be used on the test samples obtained in accordance with 7.4 [see Clause 5 list entry k)]. A test piece shall be taken from each test sample, so as to expose a prepared cross-sectional surface to the test solution.

At the completion of the test the maximum depth of dezincification in a longitudinal direction shall be measured.

8.5 Stress corrosion resistance test

The test method given in either ISO 6957:1988 (using pH 10,0) or EN 14977:2006 shall be used on the test pieces prepared from the test samples obtained in accordance with 7.4. The choice of which of these tests is used shall be at the discretion of the supplier, unless a preference is agreed at the time of the order [see Clause 5 list entry k)].

8.6 Retests

8.6.1 Analysis, tensile, hardness and dezincification resistance tests

If there is a failure of one, or more than one, of the tests in 8.1, 8.2, 8.3 or 8.4, two test samples from the same inspection lot shall be permitted to be selected for retesting the failed property (properties). One of these test samples shall be taken from the same sampling unit as that from which the original failed test piece was taken, unless that sampling unit is no longer available, or has been withdrawn by the supplier.

If the test pieces from both test samples pass the appropriate test(s), then the inspection lot represented shall be deemed to conform to the particular requirement(s) of this standard. If a test piece fails a test, the inspection lot represented shall be deemed not to conform to this document.

NOTE If an inspection lot of dezincification resistant alloys fails the dezincification resistance test when tested or retested, the supplier has the option to heat treat, or to further heat treat, the inspection lot and resubmit it for all the tests called for on the order, except for analysis.

8.6.2 Stress corrosion resistance test

If a test piece fails the test, the inspection lot represented by the failed test piece shall be permitted to be subjected to a stress relieving treatment. A further test sample shall then be selected in accordance with 7.4.

If a test piece from the further test sample passes the test, the stress relieved products shall be deemed to conform to the requirements of this standard for residual stress level and shall then be subjected to all the other tests called for on the order, except for analysis. If the test piece from the further test sample fails the test, the stress relieved products shall be deemed not to conform to this document.

8.7 Rounding of results

For the purpose of determining conformity to the limits specified in this document an observed or a calculated value obtained from a test shall be rounded in accordance with the following procedure, which is based upon the guidance given in EN ISO 80000-1. It shall be rounded in one step to the same number of figures used to express the specified limit in this document.

The following rules shall be used for rounding:

- a) if the figure immediately after the last figure to be retained is less than 5, the last figure to be retained shall be kept unchanged;
- b) if the figure immediately after the last figure to be retained is equal to or greater than 5, the last figure to be retained shall be increased by one.

9 Certificate of Compliance and inspection documentation

9.1 Certificate of Compliance

When requested and agreed at the time of the order [see Clause 5 list entry p)] the appropriate Certificate of Compliance shall be issued for the products. The relevant information is available in EN ISO/IEC 17050-1:2010 and EN ISO/IEC 17050-2:2004.

9.2 Inspection documentation

When requested and agreed at the time of the order [(see Clause 5 list entry q)] the appropriate inspection document, in accordance with EN 10204:2004 shall be issued for the products.

For pressure equipment applications, the equipment manufacturer has the obligation to request the appropriate inspection documentation according to the applicable product or application standard(s), EN 764-5:2014 and EN 10204:2004.

10 Marking, packaging, labelling

Unless otherwise specified at the time of the order, the marking, packaging and labelling shall be left to the discretion of the supplier [see Clause 5 list entry r)].

Table 1 — Composition of low alloyed copper alloys

Material designation		Composition % (mass fraction)							Density ^a g/cm ³
Symbol	Number	Element	Cu	P	Pb	S	Te	Others total ^b	approx.
CuSP	CW114C	min.	Rem.	0,003	—	0,2	—	—	8,9
		max.	—	0,012	—	0,7	—	0,1	
CuTeP	CW118C	min.	Rem.	0,003	—	—	0,4	—	8,9
		max.	—	0,012	—	—	0,7	0,1	

^a For information only.

^b Elements not reported and elements reported in the table for which no upper and lower limits are defined, are included in other totals.

Table 2 — Composition of copper-zinc alloys

Material designation		Composition ^b % (mass fraction)											Density ^a g/cm ³ approx.
Symbol	Number	Element	Cu	As	Al	Fe	Mn	Ni	Pb	Sn	Zn	Others total ^c	
CuZn40	CW509L	min.	59,0	—	—	—	—	—	—	—	Rem.	—	8,4
		max.	61,5	0,05	—	—	—	0,3	0,2	0,2	—	0,2	
CuZn42	CW510L	min.	57,0	—	—	—	—	—	—	—	Rem.	—	8,4
		max.	59,0	—	0,05	—	—	0,3	0,2	0,3	—	0,2	
CuZn38As	CW511L	min.	61,5	0,02	—	—	—	—	—	—	Rem.	—	8,4
		max.	63,5	0,15	0,05	—	—	0,3	0,2	0,1	—	0,2	

^a For information only.

^b For drinking water applications, restrictions to the chemical composition of some materials listed in this table may apply according to national regulations/laws, e.g. as specified in the 4 MS Common Composition List.

^c Elements not reported and elements reported in the table for which no upper and lower limits are defined, are included in other totals.

Table 3 — Composition of copper-zinc-lead alloys

Material designation		Composition ^b (in mass fraction)											Density ^a g/cm ³ approx.
Symbol	Number	Cu	Al	Fe	Mn	Ni	Pb	Sn	Zn	Others total ^c			
Element													
CuZn35Pb1	min.	62,5	—	—	—	—	0,8	—	Rem.	—	8,5		
	max.	64,0	0,05	0,1	—	0,3	1,6	0,1	—	0,1			
CuZn35Pb2	min.	62,0	—	—	—	—	1,6	—	Rem.	—	8,5		
	max.	63,5	0,05	0,1	—	0,3	2,5	0,1	—	0,1			
CuZn36Pb2As	min.	61,0	—	—	—	—	1,7	—	Rem.	—	8,4		
	max.	63,0	0,05	0,1	0,1	0,3	2,8	0,1	—	0,2			
CuZn36Pb3	min.	60,0	—	—	—	—	2,5	—	Rem.	—	8,5		
	max.	62,0	0,05	0,3	—	0,3	3,5	0,2	—	0,2			
CuZn37Pb1	min.	61,0	—	—	—	—	0,8	—	Rem.	—	8,5		
	max.	62,5	0,05	0,3	—	0,3	1,6	0,3	—	0,2			
CuZn37Pb2	min.	61,0	—	—	—	—	1,6	—	Rem.	—	8,4		
	max.	62,0	0,05	0,2	—	0,3	2,5	0,2	—	0,2			
CuZn38Pb1	min.	60,0	—	—	—	—	0,8	—	Rem.	—	8,4		
	max.	61,0	0,05	0,2	—	0,3	1,6	0,2	—	0,2			
CuZn38Pb2	min.	60,0	—	—	—	—	1,6	—	Rem.	—	8,4		
	max.	61,0	0,05	0,2	—	0,3	2,5	0,2	—	0,2			
CuZn39Pb0,5	min.	59,0	—	—	—	—	0,2	—	Rem.	—	8,4		
	max.	60,5	0,05	0,2	—	0,3	0,8	0,2	—	0,2			
CuZn39Pb1	min.	59,0	—	—	—	—	0,8	—	Rem.	—	8,4		
	max.	60,0	0,05	0,3	—	0,3	1,6	0,3	—	0,2			

Material designation		Composition ^b % (mass fraction)											Density ^a g/cm ³ approx.
Symbol	Number	Element	Cu	Al	As	Fe	Ni	Pb	Sn	Zn	Others total ^c		
CuZn39Pb2	CW612N	min.	59,0	—	—	—	—	1,6	—	Rem.	—	8,4	
		max.	60,0	0,05	—	0,3	0,3	2,5	0,3	—	0,2		
CuZn39Pb3	CW614N	min.	57,0	—	—	—	—	2,2	—	Rem.	—	8,4	
		max.	57,0	0,05	—	0,3	0,3	3,5	0,3	—	0,2		
CuZn40Pb2	CW617N	min.	57,0	—	—	—	—	1,6	—	Rem.	—	8,4	
		max.	59,0	0,05	—	0,3	0,3	2,2	0,3	—	0,2		
CuZn35Pb1,5AlAs	CW625N	min.	62,0	0,5	0,02	—	—	1,2	—	Rem.	—	8,4	
		max.	64,0	0,7	0,15	0,1	0,2	1,6	0,3	—	0,2		
CuZn33Pb1,5AlAs	CW626N	min.	64,0	0,8	0,02	—	—	1,2	—	Rem.	—	8,4	
		max.	66,0	1,0	0,15	0,1	0,2	1,7	0,3	—	0,2		
CuZn40Pb1	CW627N	min.	57,0	—	—	—	—	0,8	—	Rem.	—	8,4	
		max.	59,0	0,05	—	0,3	0,3	1,6	0,3	—	0,2		

^a For information only.

^b For drinking water applications, restrictions to the chemical composition of some materials listed in this table may apply according to national regulations/laws, e.g. as specified in the 4 MS Common Composition List.

^c Elements not reported and elements reported in the table for which no upper and lower limits are defined, are included in other totals.

Table 4 — Composition of complex copper alloys

Material designation		Composition ^b (% mass fraction)													Density ^a g/cm ³ approx.
Symbol	Number	Cu	Al	As	Fe	Mn	Ni	P	Pb	Si	Sn	Zn	Others total ^c		
CuZn32Pb2AsFeSi	min.	64,0	—	0,03	0,1	—	—	—	1,5	0,45	—	Rem.	—	8,4	
	max.	66,5	0,05	0,08	0,2	—	0,3	—	2,2	0,8	0,3	—	0,2		
CuZn37Mn3Al2PbSi	min.	57,0	1,3	—	—	1,5	—	—	0,2	0,3	—	Rem.	—	8,1	
	max.	59,0	2,3	—	1,0	3,0	1,0	—	0,8	1,3	0,4	—	0,3		
CuZn40Mn1Pb1	min.	57,0	—	—	—	0,5	—	—	1,0	—	—	Rem.	—	8,3	
	max.	59,0	0,2	—	0,3	1,5	0,6	—	2,0	0,1	0,3	—	0,3		
CuZn40Mn1Pb1AlFeSn	min.	57,0	0,3	—	0,2	0,8	—	—	0,8	—	0,2	Rem.	—	8,3	
	max.	59,0	1,3	—	1,2	1,8	0,3	—	1,6	—	1,0	—	0,3		
CuZn40Mn1Pb1FeSn	min.	56,5	—	—	0,2	0,8	—	—	0,8	—	0,2	Rem.	—	8,3	
	max.	58,5	0,1	—	1,2	1,8	0,3	—	1,6	—	1,0	—	0,3		
CuZn21Si3P	min.	75,0	—	—	—	—	—	0,02	—	2,7	—	Rem.	—	8,3	
	max.	77,0	0,05	—	0,3	0,05	0,2	0,10	0,10	3,5	0,3	—	0,2		
CuZn33Pb1AlSiAs	min.	64,0	0,1	0,04	—	—	—	—	0,4	0,1	—	Rem.	—	8,5	
	max.	67,0	0,3	0,08	0,3	0,04	0,2	0,02	0,9	0,3	0,3	—	0,2		
CuZn36Si1P	min.	60,5	—	—	—	—	—	0,01	—	0,7	—	Rem.	—	8,3	
	max.	64,5	—	—	0,2	0,2	0,2	0,10	0,10	1,3	0,2	—	0,3		

^a For information only.^b For drinking water applications, restrictions to the chemical composition of some materials listed in this table may apply according to national regulations/laws, e.g. as specified in the 4 MS Common Composition List.^c Elements not reported and elements reported in the table for which no upper and lower limits are defined, are included in other totals.

Table 5 — Mechanical properties of low alloyed copper alloys

Designations		Material condition	Thickness		Tensile strength R_m N/mm ² (MPa)	0,2% proof strength $R_{p0,2}$ N/mm ² (MPa)	Elongation A %	Hardness			
			from	over				up to and including	min.	max.	min.
CuSP CuTeP	Number CW114C CW118C	M	All	All	—	—	—	80	130	90	140
		H080	All	All	—	—	—	80	130	90	140

https://www.khina-ganges.com/

Table 6 — Mechanical properties of copper alloys

Designations		Thickness		Elongation	Hardness				
		from	over		min.	max.	min.	max.	
Material	Condition	mm		A	HV				
		up to	including		min.	max.	min.	max.	
Symbol	Number			%	HBW				
					min.	max.	min.	max.	
	M	All		As manufactured					
	R360	2	20	360	—	300	—	—	—
	H070	2	20	—	—	—	70	100	80
	R410	2	10	410	250	—	—	—	—
	H100	2	10	—	—	—	100	145	110
	R500	2	7	500	350	—	—	—	—
	H120	2	7	—	—	—	120	—	130
CuZn40	CW509L								

Designations		Material condition	Thickness		Tensile strength R_m N/mm ² (MPa)	0,2 % proof strength $R_{p0.2}$ N/mm ² (MPa)	Elongation A %	Hardness					
Material	Number		mm over	up to and including				min.	max.	min.	max.		
CuZn42	CW510L	M	All	All	As manufactured								
		R360	2		40	360	—	320	20	—	—		
		H090	2		40	—	—	—	—	90	125	100	135
		R430	2		15	430	220	—	10	—	—	—	—
		H110	2		15	—	—	—	—	110	160	120	170
		R500	2		7	500	350	—	8	—	—	—	—
		H135	2		7	—	—	—	—	135	—	145	—
CuZn38As	CW511L	M	All	All	As manufactured								
		R280	2		All	280	—	200	30	—	—	—	—
		H070	2		All	—	—	—	—	70	110	80	120
		R320	2		20	320	200	—	20	—	—	—	—
		H090	2		20	—	—	—	—	90	135	100	145
		R400	2		8	400	250	—	8	—	—	—	—
		H105	2		8	—	—	—	—	105	—	115	—

Table 7 — Mechanical properties of copper-zinc alloys

Designations		Thickness		Tensile strength R_m N/mm ² (MPa)	0,2% proof strength $R_{p0,2}$ N/mm ² (MPa)	Elongation A %	Hardness	
Material	Material condition	from mm	over mm up to and including				HBW	HV
Symbol	Number	from		min.	max.	min.	min.	max.
	M	All		As manufactured				
	R280	2	All	280	—	200	—	—
CuZn36Pb2As	H070	2	All	—	—	—	70	110
CuZn35Pb1,5AlAs	R320	2	20	320	200	—	—	—
CuZn33Pb1,5AlAs	H090	2	20	—	—	—	90	135
	R400	2	8	400	250	—	—	—
	H105	2	8	—	—	—	105	115

Designations		Material condition	Thickness		Tensile strength R_m N/mm ² (MPa)	0,2 % proof stress $R_{p0,2}$ N/mm ² (MPa)	Elongation A %	Hardness		
Material	Number		mm over	up to and including				min.	max.	min.
		M	All	All	As manufactured					
CuZn35Pb2 CuZn36Pb3 CuZn37Pb1 CuZn37Pb2		R340	2	20	340	—	280	—	—	—
		H070	2	20	—	—	—	70	120	80
		R400	2	10	400	200	—	—	—	—
		H100	2	10	—	—	—	100	140	110
		R480	2	7	480	350	—	—	—	—
	H125	2	7	—	—	—	125	—	135	—
		M	All	All	As manufactured					
CuZn38Pb1 CuZn38Pb2 CuZn39Pb1 CuZn39Pb2		R360	2	20	360	—	300	—	—	—
		H070	2	20	—	—	—	70	100	80
		R410	2	10	410	250	—	—	—	—
		H100	2	10	—	—	—	100	145	110
		R500	2	7	500	350	—	—	—	—
	H120	2	7	—	—	—	120	—	130	—

Designations		Thickness		Tensile strength	Proof strength	Elongation	Hardness		
Material	Symbol	Material condition		R_m N/mm ² (MPa)	$R_{p0,2}$ N/mm ² (MPa)	A %	HBW		HV
		from	up to and including				min.	max.	
		All					As manufactured		
		M							
		2	40	360	—	20	—	—	—
		2	40	—	—	—	90	125	100
		2	15	430	220	10	—	—	—
		2	15	—	—	—	110	160	120
		2	7	500	350	8	—	—	—
		2	7	—	—	—	135	—	145

<https://www.hansa-gardes.com/>

Table 8 — Mechanical properties of complex copper-zinc alloys

Designations		Thickness		Tensile strength R_{m} N/mm ² (MPa)	Elongation		Hardness			
					Material condition	Number	A %	HBW		HV
from	over	min.	max.	min.				max.	min.	max.
CuZn32Pb2AsFeSi	M	All		As manufactured						
		3	15	380	220	—	—	—	—	
		3	15	—	—	—	110	150	120	160
		3	10	430	260	—	—	—	—	—
		3	10	—	—	—	120	170	130	180
CuZn37Mn3Al2PbSi	M	All		As manufactured						
		10	30	540	280	—	—	—	—	—
		10	30	—	—	—	130	170	140	180
		5	10	590	320	—	—	—	—	—
		5	10	—	—	—	150	190	160	200

Designations		Thickness		Tensile strength	Elongation	Hardness		
						HBW	HV	
Material	Symbol	Material condition	mm	R _m N/mm ² (MPa)	A %	proof strength		
						R _{p0,2} N/mm ² (MPa)	%	
Material	Number	Material condition	mm	min.	max.	min.	max.	
			from					over
CuZn40Mn1Pb1	CW720R	M	All	As manufactured	As manufactured	As manufactured	As manufactured	
		R390	10	30	390	180	—	—
		H090	10	30	—	—	90	125
		R440	5	10	440	250	—	—
		H100	5	10	—	—	100	145
CuZn40Mn1Pb1AlFeSn CuZn40Mn1Pb1FeSn	CW721R CW722R	M	All	As manufactured	As manufactured	As manufactured	As manufactured	
		R440	10	30	440	180	—	—
		H100	10	30	—	—	100	140
		R500	5	10	500	270	—	—
		H130	5	10	—	—	130	140

Designations		Material condition	Thickness		Tensile strength R _m /mm ² (MPa)	0,2 % proof strength R _{p0,2} N/mm ² (MPa)		Elongation A %	Hardness		
			mm over	up to and includin g		min.	max.		min.	max.	min.
Symbol	Number								HBW	HV	
CuZn21Si3P	CW724R	M	All								
		R500	2	20	500	—	450	15	—	—	
		H130	2	20	—	—	—	—	130	180	190
		R600	2	20	600	350	—	12	—	—	—
		H150	2	20	—	—	—	—	150	220	160
		R650	2	7	650	400	—	10	—	—	—
		H170	2	7	—	—	—	—	170	—	180
CuZn33Pb1AlSiAs	CW725R	M	All								
		R290	2	All	290	—	200	30	—	—	
		H070	2	All	—	—	—	—	70	110	80
		R320	2	20	320	200	—	20	—	—	—
		H090	2	20	—	—	—	—	90	135	100
		R400	2	8	400	250	—	8	—	—	—
		H105	2	8	—	—	—	—	105	—	115

<http://www.chinacang.com>

Designations		Thickness		Tensile strength	Elongation	Hardness		
						HBW	HV	
Material	Material condition	mm	mm	R _m N/mm ² (MPa)	A %	R _{p0,2} N/mm ² (MPa)	%	
								Symbol
CuZn36Si1P	M	All		As manufactured				
	R460	2	20	460	15	—	—	—
	H100	2	20	—	—	—	100	180
	R510	2	20	510	10	270	—	—
	H130	2	20	—	—	—	130	210
	R580	2	7	580	3	420	—	—
	H150	2	7	—	—	—	150	160

Table 9 — Tolerances on external diameter or width across-flats

Dimensions in millimetres

Nominal external diameter or width across-flats		Tolerances on diameter or width across-flats ^a		
over	up to and including	class A	class B	class C
12 ^a	18	—	0 -0,18	0 -0,11
18	30	±0,24	0 -0,21	0 -0,13
30	50	±0,31	0 -0,25	0 -0,16
50	80	±0,60	0 -0,46	0 -0,30
80	140	±1,0	±0,80	±0,50

NOTE Products supplied to class B and class C tolerances will normally be drawn finish.

^a Including 12.

^b For deviation from circular form refer to 6.5.4.1, for deviation from polygonal cross-section form refer to 6.5.4.2.

Table 10 — Tolerances on wall thickness

Nominal wall thickness		Tolerance on wall thickness expressed as a percentage of nominal wall thickness
over	up to and including	
2 ^a	3	±12
3	6	±10
6	10	±9
10	—	±8

^a Including 2.

Table 11 — Tolerances on diameter of the bore

Dimensions in millimetres

Nominal bore diameter		Tolerances on bore diameter ^b	
over	up to and including	class A	class B
8 ^a	10	±0,29	±0,11
10	18	±0,35	±0,14
18	30	±0,42	±0,17
30	50	±0,80	±0,20
50	70	±0,95	±0,37
70	120	±1,50	±0,50

NOTE Products supplied to class B tolerances will normally be drawn finish.

^a Including 8.

^b For deviation from circular form refer to 6.5.4.1.

Table 12 — Tolerances on eccentricity

Nominal wall thickness <i>WT</i> mm	Maximum eccentricity %
$2 < WT \leq 3$	10
$WT > 3$	8

Table 13 — Tolerances on straightness of hollow rod

Nominal external diameter or width across-flats	Maximum deviation from straightness (see 6.5.5 - Figure 2) mm			
	depth of arch in any length <i>l2</i> of 400 mm		depth of arch in any length <i>l1</i> of 1000 mm	
	for alloys in Tables 2 and 3	for alloys in Tables 1 and 4	for alloys in Tables 2 and 3	for alloys in Tables 1 and 4
Round external shape				
from 12 mm up to and including 50 mm	0,7	1,4	1,5	3,0
Polygonal external shape				
from 12 mm up to and including 50 mm	1,0	2,0	2,0	4,0
NOTE 1 The tolerances of straightness shown in the table only apply to material condition foreseen in this standard.				
NOTE 2 The permissible deviation for hollow bars in extruded form shall be agreed between the involved parties				
NOTE 3 The tolerances of straightness for nominal external diameters or width across-flats bigger than 50 mm shall be agreed between the involved parties.				

Table 14 — Tolerances on length of hollow rod

Dimensions in millimetres

Nominal external diameter or width across-flats		Preferred (available) lengths	Tolerance on length
over	up to and including		
—	30	3 000 and 4 000	±50
30	50	2 500 and 3 000	±100
50	80	2 000 and 3 000	±100
NOTE The tolerance on length for nominal external diameter or width across-flats bigger than 80 mm shall be agreed between the involved parties.			

Table 15 — Corner radii for hollow rod with square, hexagonal or octagonal external shape

Dimensions in millimetres

Nominal width across-flats		Radii for sharp and rounded corners	
over	up to and including	sharp max.	rounded range
12 ^a	18	0,5	0,5 to 1,2
18	30	0,6	0,6 to 1,8
30	50	0,7	0,7 to 2,8
50	60	0,8	0,8 to 4,0

NOTE The corner radii for nominal width across-flats bigger than 60 mm shall be agreed between the involved parties.

^a Including 12.

Table 16 — Maximum twist for hollow rod with square, hexagonal or octagonal external shape

Dimensions in millimetres

Nominal width across-flats <i>W</i>		Maximum permitted twist <i>V</i> in any 1 m length of rod
over	up to and including	
12 ^a	18	1,0
18	30	2,0
30	60	3,0

NOTE The maximum twist for nominal width across-flats bigger than 60 mm shall be agreed between the involved parties.

^a Including 12.

Table 17 — Sampling rate

Ordered nominal dimensions (external diameter or width across-flats) mm		Size of inspection lot for one test sample kg
over	up to and including	
—	25	1 000
25	—	2 000

NOTE Larger quantities require sampling in proportion, up to a maximum of three test samples.

Table 18 — Acceptance parameters for reference standard

Dimensions in millimetres

Hollow Rod size		Hole diameter	Hole depth (min.)
over and including	up to		
5	10	1,0 ± 0,05	0,8
10	40	1,5 ± 0,05	0,8
40	50 ^a	2,0 ± 0,05	0,8

NOTE The acceptance parameters for the hollow rod sizes bigger than 50 mm shall be agreed between the involved parties.

^a Including 50.

Table 19 — Acceptance criteria (surface classes) for eddy current testing

Dimensions in millimetres

Hollow Rod size		class A		class B	
over and including	up to	K2	d ₀ ^b	K2	d ₀ ^b
5	10	0,6	0.020	0,4	0.050
10	40	0,6	0.027	0,4	0.067
40	50 ^a	0,6	0.033	0,4	0.083

NOTE The acceptance criteria for the hollow rod sizes bigger than 50 mm shall be agreed between the involved parties.

^a Including 50.
^b Maximum density d0 referred to a pre-set length of 300 mm.

Annex ZA
(informative)

Relationship between this European Standard and the essential requirements of Directive 2014/68/EU (Pressure equipment Directive) aimed to be covered

This European Standard has been prepared under a Commission's standardization request M/601 to provide one voluntary means of conforming to essential requirements of Directive 2014/68/EU.

Once this standard is cited in the Official Journal of the European Union under that Directive, compliance with the normative clauses of this standard given in Table ZA.1 confers, within the limits of the scope of this standard, a presumption of conformity with the corresponding essential requirements of that Directive and associated EFTA regulations.

For this harmonized supporting standard for materials, presumption of conformity to the Essential Requirements of the Directive is limited to technical data of the material in the standard and does not presume adequacy of the material to specific equipment. Consequently, the technical data stated in the material standard should be assessed against the design requirements of the specific equipment to verify that the Essential Requirements of the Pressure Equipment Directive (PED) are satisfied.

Table ZA.1 — Correspondence between this European Standard and Annex I of Directive 2014/68/EU (Pressure equipment Directive)

Essential Requirements of Directive 2014/68/EU	Clause(s)/subclause(s) of this EN	Remarks/Notes
4.1 (a)	6.2	Mechanical properties
4.3	9.2, 2 nd paragraph	Conformity of material and manufacturer's certified documentation

WARNING 1 — Presumption of conformity stays valid only as long as a reference to this European Standard is maintained in the list published in the Official Journal of the European Union. Users of this standard should consult frequently the latest list published in the Official Journal of the European Union.

WARNING 2 — Other Union legislation may be applicable to the product(s) falling within the scope of this standard.

Bibliography

- [1] EN 1173:2008, *Copper and copper alloys — Material condition designation*
- [2] EN 1412:2016, *Copper and copper alloys — European numbering system*
- [3] EN 12163, *Copper and copper alloys — Rod for general purposes*
- [4] EN 12449, *Copper and copper alloys — Seamless, round tubes for general purposes*
- [5] EN ISO 9001, *Quality management systems — Requirements (ISO 9001)*
- [6] EN ISO 80000-1, *Quantities and units — Part 1: General (ISO 80000-1)*
- [7] EN ISO/IEC 17050-1:2010, *Conformity assessment — Supplier's declaration of conformity — Part 1: General requirements (ISO/IEC 17050-1:2004)*
- [8] EN ISO/IEC 17050-2:2004, *Conformity assessment — Supplier's declaration of conformity — Part 2: Supporting documentation (ISO/IEC 17050-2:2004)*
- [9] ISO 1190-1:1982, *Copper and copper alloys — Code of designation — Part 1: Designation of materials*
- [10] ISO 1811-2, *Copper and copper alloys — Selection and preparation of samples for chemical analysis — Part 2: Sampling of wrought products and castings*
- [11] "Acceptance for metallic materials used for products in contact with drinking water", 4 MS Common approach, Part B "4 MS Common Composition List"
(<https://www.umweltbundesamt.de/themen/wasser/trinkwasser/trinkwasser-verteilen/anererkennung-harmonisierung-4ms-initiative>)

<https://www.china-gauges.com/>

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than one device provided that it is accessible by the sole named user only and that only one copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than one copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright and Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email cservices@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email: cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

<https://www.china-gauges.com/>